

N.U.Q.Q.

NEW ULM QUARTZITE QUARRIES

2009 PRODUCT TEST SUMMARY

PRODUCT: MNDOT CA - 5, (3/4" x #4)

GRADATION

NUMBER OF TESTS PERFORMED: 5			DATE OF LAST TEST: 07/21/2009			
SIEVES (millimeters in parentheses)	MNDOT SPEC LIMITS	MNDOT SPEC MEDIAN	N.U.Q.Q. RUNNING AVERAGE	SAMPLE STANDARD DEVIATION ABOUT RUNNING AVERAGE	N.U.Q.Q. PRODUCTION WORKING RANGE	% OF FOUR CONSECUTIVE TESTS INSIDE OF WORKING RANGE
1.0" (25.0)	100%		100.0%	0.0%	100%	100.0%
0.75" (19.0)	85% - 100%	92.5%	100.0%	0.0%	100% - 100%	100.0%
0.5" (12.5)			71.0%	5.5%	65% - 77%	100.0%
0.375" (9.5)	30% - 60%	45.0%	38.0%	5.5%	32% - 43%	100.0%
#4 (4.75)	0% - 10%	5.0%	3.9%	0.9%	3% - 5%	100.0%
M.N.D.O.T. CA-5 will meet A.S.T.M. #67 specification for gradation.						
NOTE: VALUES INDICATE THE PERCENT BY WEIGHT PASSING SQUARE OPENING SIEVES.						

GENERAL QUALITY

QUALITY PARAMETERS	N.U.Q.Q. RUNNING AVERAGE	MNDOT SPEC LIMITS	NOTE
NON CLASS 'A' MATERIAL BY WEIGHT:	1.0%	4.0% MAX.	SANDSTONE
L.A.R. ABRASION LOSS, (A.S.T.M. C131-89):	31.2%	40% MAX.	TOUGHNESS
MAGNESIUM SULFIDE LOSS, (A.S.T.M. C88-90 - 5 CYCLES):	4.8%	15% MAX.	SOUNDNESS
FLAT & ELONGATED PARTICLES, (A.S.T.M. D-4791):	0.0%		RATIO: 3:1
SPECIFIC GRAVITY, (A.S.T.M. C127-88):	2.63 / 2.66 / 2.64	N/A	BULK / APPARENT / SSD
ABSORPTION IN BULK SAMPLE, (A.S.T.M. C126):	< 0.43%	N/A	POROSITY
UNIT WEIGHT, PCF, (A.S.T.M. C29):	88.4 / 82.3	N/A	DRY RODDED / LOOSE
VOIDS, %, (A.S.T.M. C29):	46.0% / 49.8%	N/A	DRY RODDED / LOOSE
FREEZE THAW DURABILITY, (A.S.T.M. 666 METH. A, 306 CYCLES):	88.5% / 0.006%	N/A	RDME / LENGTH CHANGE
A.S.R. EXPANSION, (A.S.T.M. C-1260-94 @ 14 DAYS):	0.220%		A.S.R. REACTIVITY
200 MESH, (75 MICRON), MATERIAL, (A.S.T.M. C117-90):	0.3%	0.8% MAX.	SURFACE DUST
QUARTZITE AGGREGATES CONTAIN NO SHALE, IRON OXIDE, SLATE, UNSOUND CHERT OR CLAY BALLS.			

NEW ULM QUARTZITE QUARRIES, INC.
PHONE: (507) 354-2925; FAX: (507) 359-7870
45755 571st Lane , NEW ULM, MN 56073
SAMPLES AVAILABLE UPON REQUEST